

INSTALLATION GUIDELINES - ECOWORX BROADLOOM

We think giving you the very best for your carpet dollar is a three-step process: making it, installing it, and maintaining it. And while the making it is often the primary focus of manufacturers, the installation and maintenance procedures can make or break the beauty of your installation as well.

That's why The New Patcraft & Designweave provides a detailed and comprehensive guide to carpet installation. It covers the basics-like the importance of checking out the products before any cuts are made – to more esoteric tips like the need to always align the center of diamond designs when matching for pattern.

With our guidance and careful attention to detail, a qualified installer will provide you with the kind of installation you need to enjoy years and years of service from your carpet from The New Patcraft & Designweave.



NOTICE – FAILURE TO FOLLOW THESE GUIDELINES CAN RESULT IN VOIDING THE CARPET WARRANTY.

NOTICE: LOOK BEFORE YOU CUT.....

Contact your Sales Representative or the Financial Services Department if a visible Manufacturing defect exists. If such a defect is Installed, Shaw is not liable for the installation.

Installation Guidelines

The following instructions shall be reviewed prior to installation. Shaw will not be responsible for improper installation.

Site Testing and Conditioning

Maintain the temperature of the installation site, carpet, adhesive and seam sealer between 65° F and 95° F for 24 hours before installation. Do not begin the installation if the room or subfloor temperature is below 65° F. The adhesive and seam sealer will not function properly when applied over an extremely cold surface. Relative humidity should not exceed 65%. These conditions must be maintained for 24 hours prior to, during and 24 hours after installation.

Test the slab for moisture and alkalinity prior to beginning the installation. Check the concrete for surface pH at several locations. A reading below 5.0 or above 9.0 requires corrective measures. Specific information on the correct method of neutralizing extremely low or high pH is available from the Shaw Field Technical Services Department.

Check the concrete for moisture at several locations using anhydrous calcium chloride test kits. The moisture transmission rate must not exceed 5.0 lbs. per 1000 sq. ft. per 24 hours. Do not begin the installation if a higher moisture transmission rate is detected. Do not use other methods of moisture testing, as they are not reliable. If moisture is excessive advise the general contractor or building owner for a decision on whether to begin.

Shaw is not responsible for any moisture related installation failures if these guidelines are not strictly followed.

Floor Preparation

The floor must be free of dust, dirt, oil, grease, paint, wax, moisture or any debris that could affect adhesion of these backings to the floor. Do not use sweeping compounds as they may leave an oily residue that can prevent adhesive from bonding to the sub floor.

The floor must be level and smooth. Depressions and cracks must be filled with a liquid latex additive patching compound and all protrusions leveled. Any previous adhesives need to be removed to a bonded residue. **NOTE: Do not sand or scrape Vinyl-asbestos tile (VAT)** without proper attention to asbestos abatement procedures and precautions in accordance with all state and local codes.



SHAW ACCEPTS NO RESPONSIBILITY IF LOOSE ASBESTOS CONTAINING FLOORINGS ARE AFFECTED UPON REMOVAL OF CARPETING.

Concrete floors must be sealed if dusting or powdering exists. The following floor sealers are suggested for concrete: Shaw 9050 Floor Sealer and Shaw 8550 Level Primer.

Adhesives

Shaw recommends the use of Shaw 3500 or 3600 (AATCC174) adhesives or equivalent adhesives, which have been formulated with a higher solids content and will perform adequately with the Eco Broadloom Backings. Use of other adhesive could result in an installation failure. Any claims resulting from installation failures due to adhesives should be directed to the applicable adhesive manufacturer. For information regarding equivalent adhesives, please contact Shaw at 1.877.471.7429.

Recommended Application:

Pattern Products - 1/8" x 1/8" x 1/8" "U" notch trowel providing a coverage rate of 5 - 7 yds/gal (container size 4 – gallon) depending on the porosity of the substrate.

Non – Pattern Products -3/32" x 3/32" u-notch trowel or equivalent that will provide a coverage rate of 8-9 yds/gal (container size 4- gallon) depending on the porosity of the substrate.

On extremely porous or floors with residual multi-purpose adhesive, more adhesive will be needed. Coverage rates should be closely monitored. Excessive rates may indicate a worn or improperly notched trowel.

Due to the high solids content of these adhesives a reduced set up time can be expected. Adhesive open time will vary depending on the temperature and humidity at the job site. The adhesive is ready for carpet installation when the entire ridge of glue becomes tacky. This can be checked by firmly placing a finger into the ridge of adhesive and pressing to the floor. Lift slowly and the adhesive should stick to the floor and your finger and have leg or strings for one to two inches. Fans or air movers blowing across not on the adhesive will greatly reduce required open time.

Inadequate adhesive application or set up time may result in bubbles and/or peaked seams and repair will require more time and effort than proper initial installation.

Job Layout

Dry lay the entire area to be carpeted. Implement roll sequencing prior to cutting any textured, graphic product. Dry laying will minimize the normal variations encountered when pattern matching and reveal any bow or skew within the roll. Follow the roll numbers sequentially. If the roll information has been removed prior to the carpet arriving on the job site, the date and time is back-stamped (in military time) on the carpet to assist in sequencing.



Rolling

This backing should be rolled widthwise, and then lengthwise with a 75–100 lb. roller to assure transfer of the adhesive between floor and carpet backing and to eliminate any trapped air. Failure to perform this could result in bubbling or unwanted air pockets.

Cutting and Seaming

Seam edges shall be trimmed using tools and techniques best suited for the carpet. Trim edges far enough into the material, normally about 8-10 rows, to maintain the structural integrity of the carpet. The cutting technique for this backing system is row cut both edges. Correct pattern matching, gaps and overlaid areas with use of a knee kicker, power stretcher, deadman, Roberts 10-117 or equivalent ministretcher and stay nails.

Patterned carpets must be cut by the row cut/row cut method and dry laid to ensure pattern match, also check for sidematch and any visual defects.

Use a screwdriver or awl to separate rows of yarn and cut with a cushion back or loop pile cutter. After the adhesive has become tacky, place the first drop into the adhesive and apply seam sealer, following with the second breadth pattern matching if necessary. Use of a power stretcher, deadman, Roberts 10-117 or equivalent mini stretcher and stay nails may be required to obtain proper match. Remove stay nails after the adhesive set-up – approximately 12-24 hours after installation.

Cross seams can be made the same as side seams if the rows can be run across the width. If not, cut both sides of the carpeting on pattern and proceed to pattern match the seam.

Seam Sealing

All commercial broadloom products <u>require</u> the use of a latex seam sealer such as Shaw 4000 or a polymer sealer such as Shaw 8300 (providing a moisture impervious seam). Seam sealer must be applied to the edges trimmed for seaming, and cover the thickness of both the primary and secondary backing without contaminating the face yarn.

CAUTION: Seam edges **must** be sealed to prevent edge ravel, tuft loss, and delamination of the secondary backing in the seamed area.

Steaming

In order to alleviate bubbles, creases, pile distortion and crushing, it is advised to steam the carpet. Successful steaming is dependent on an adequate application of adhesive. Shaw recommends the use of a wallpaper steamer that has a 12" plastic head. Wallpaper steamers can be obtained through any local hardware store and can also be rented for a minimal charge. A white cotton cloth should be placed under the head of the steamer to protect the carpet fiber. Placing the steamer on the affected area for approximately 45 sec. – 1 min. will allow the carpet backing to become pliable and reactivate the adhesive in order to assist in removal of the bubbles, creases or pile distortion. When the carpet is properly steamed, the affected area should be rolled with a carpet tractor to create a bond between



the carpet backing and adhesive. It may be necessary to repeat this process in order to alleviate an area displaying bubbles. If steaming does not correct the bubbled areas, then an application of adhesive to the affected area may be necessary. Allowing adequate adhesive tack time will insure proper adhesion.

Note – If the steamer is left for a prolonged period of time on the carpeting, it could potentially cause the carpet fiber to appear darker. As the carpeting dries and the moisture dissipates the carpet will regain its original color.

Transitions

Where carpet meets other floor coverings, the edges must be adequately protected with an appropriate transition molding or strip that covers the carpet edge at least ½".

Post Installation Care and Protection

- Use plywood over the carpet when heavy objects are moved within 24 hours after installation.
- Protective chair mats under chairs with casters are recommended. This will prevent excessive wear to the face of the carpeting.
- A non-staining building material paper must be placed over the carpet to protect it when additional construction activity is to take place that could soil or stain it. Do not use plastic sheeting as it could trap moisture. The self sticking type can transfer adhesive residue to the carpet that will attract t soil.

These installation procedures are intended to assist in the installation and care of Shaw carpet under most job conditions. Specific questions regarding installation and maintenance not covered must be referred to the **Shaw Technical Services Department at 1-800-471-7429**. Any variance from these procedures will become the responsibility of the installer and not Shaw Inc.

Shaw Technical Bulletins are updated as new information becomes available. To determine if this represents the most current information, call 1-800-471-7429 and ask for the current bulletin number and date. **SPD02-06/25/08**.

Technical Services Phone Numbers and Web Sites

1-800-471-7429

Shaw Contract Group shawcontractgroup.com
The New Patcraft & Designweave thenewpatcraftdesignweave.com



Bow, Skew, and Pattern Elongation

Q: How do you install a patterned carpet if it has bow, skew, or pattern elongation that is within the set tolerances of 1½" for bow in 12', 1½" for skew in 12', and 1½" for pattern elongation in 12'?

A: First, dry lay all the carpet according to roll or pattern sequence. The sequence number on the roll tag determines installation sequence if a pattern sequence is not provided. Dry stretch the carpet to minimize alignment difficulties. For bow or skew, select the most prominent width wall, cut the carpet exactly on pattern across the width, then position the carpet along the wall. If cut and positioned correctly, either the bowed or skewed edge(s) will be running up the wall. Fold the carpet back and spread the recommended adhesive using the proper trowel size. Allow the adhesive to properly tack to develop good adhesive legs.

Using the mini stretcher, pull the skewed or bowed edge down off the wall. Align the pattern along the wall. This will form a bubble that will need to be moved to the opposite end of the seam. A bowed carpet will form a bubble on both edges, a skew will bubble only on one side. Align the pattern as the bubble is moved down the seam. It may be necessary to over stretch the carpet pattern with the mini stretcher and allow it to slide back to achieve proper alignment. Use a power stretcher and "deadman" to properly align the pattern along the opposite wall. A "deadman" is constructed by nailing tack strip completely on one side of a 2"x12"x 4' long piece of lumber. If necessary, stay nails can be used to hold the pattern in place. Remove the nails after adhesive has set.

For pattern elongation, start at the center of the drop and match the pattern at the seam. Then, working both ways from the center out toward the opposite walls, use the mini stretcher or power stretcher to stretch and align pattern working towards each wall.