

KOVARA™ 95

Moisture barrier for protection of flooring assemblies up to 95% relative humidity

Product description

KOVARA™ 95 is a moisture barrier designed to be laid down above concrete floor slabs and below floor coverings to protect these materials — as well as their adhesives — from any staining, warping or mold that may result from water vapor emissions and alkaline salts infiltrating through the concrete slab up to 95% relative humidity.

KOVARA™ 95 consists of a three-layer composite construction, with a HDPE bottom layer for moisture protection, glass mat middle layer for dimensional stability, and gray mineral top layer to enhance adhesive bond.

KOVARA™ 95 is installed with KOVARA™ 95 Seam Tape to protect the seams. When moderate or heavy rolling loads are expected, application of KOVARA™ Double Sided Tape is required in a 5' x 5' or 2.5' x 2.5' box grid configuration. Refer to the KOVARA™ Box Grid Application Method on gcpat.com for additional information.

Product Advantages

- Installation in a fraction of the time of epoxy-based moisture barriers
- Reduced labor costs and improved project capacity for contractors
- Reduced downtime and business disruption for building owners
- No shotblasting required
- Resistant to heavy rolling loads
- No VOCs (per California Specification 01350)
- Does not support mold or mildew growth
- 10-year product warranty

Warranty

KOVARA™ moisture barriers are backed by a limited 10-year replacement warranty. You can find the entire KOVARA™ 95 warranty information at gcpat.com, or contact your GCP Applied Technologies sales representative for details.

Technical Services

KOVARA™ 95 customers benefit from GCP's Technical Service team, providing field support for successful job completion.

transforming performance.

Product uses

KOVARA™ 95 can be used under any of these approved floor coverings:

- Carpet tile
- LVT/LVP-luxury vinyl tile/luxury vinyl plank
- SDT-static dissipative tile
- Laminate flooring
- Engineered wood

The following specialty floors require review to verify existing conditions and use to ensure the best installation; please contact your local GCP flooring sales rep or GCP Technical Services for a warranty registration form or any other questions.

- Commercial and residential sheet vinyl flooring
- Rubber flooring
- Resilient sports flooring
- Wood court flooring
- Installations Guidelines

Slab RH Testing and Pre-Installation Requirements

All concrete slabs, regardless of grade, should be tested for moisture content using the approved method of RH in-situ probe testing in accordance to the latest version of ASTM F-2170. Slabs should only be tested 28 days after pour and once the slab has been allowed to realize appropriate service conditions, which includes permanent heat/HVAC operations and complete enclosure of the space.

Acclimate all flooring materials and adhesives in accordance with the flooring manufacturer's recommendation. Floors and the planned installation space should be conditioned at least 48-72 hours prior to the start of the installation. Environmental conditions should remain constant during the installation and after the installation is completed. Permanent HVAC should be in operation and set to between 65°F - 85°F.

Always inspect KOVARA™ 95, KOVARA™ tapes, and flooring materials for physical damage and/or defects. The installation of defective or damaged materials, in most cases, may deny any future rights to a claim.

KOVARA™ 95 installations, including floor preparation and finished flooring, should not be started or installed where further trade work on or above the product will be required. Always read the associated documentation and installation instructions for all flooring, adhesives and underlayment to be installed.

transforming performance.

All waxes and/or sealers should be removed using industry approved methods prior to the installation of KOVARA™ tapes and encapsulation with KOVARA™ 95.

KOVARA™ 95 Installation

Apply KOVARA™ 4" double-sided tape at all doorways and transitions to other flooring materials to prevent air from entering below the system or movement of the KOVARA™ 95. If the floor to be installed will be heavily trafficked or used with heavy rolling loads, please refer to the Box Grid Application Method before continuing.

Evaluate the layout of the KOVARA™ 95 to ensure minimal waste. Unroll the KOVARA™ 95 starting at a wall. Be sure that the smooth, glossy side is facing the substrate (down) and the rough-textured side is facing up. Net fit to walls and trim to fit. Individual cuts should not exceed 30 linear feet in length.

Repeat the previous steps to complete the layout of subsequent pieces, ensuring that the end cuts are staggered to allow the offset of cross seams.

Working from one side of the room, lightly butt the pieces of the KOVARA™ 95 together and tape all seams with KOVARA™ 95 seam tape. Complete by rolling all seams with either a hand roller or 75-100 pound resilient roller. NEVER OVERLAP SEAMS as it may telegraph through the finished flooring, and NEVER USE COMPRESSION METHOD at any seams.

When installing around floor monuments, columns, or poles, splice the KOVARA™ 95 to fit around the obstructions and tape to secure the seams in this area.

Finished Flooring Installation

Sweep the KOVARA™ 95 membrane to remove any installation debris, dust or dirt that may have accumulated during the application. Complete the finished flooring installation in accordance with all manufacturer guidelines. Apply the adhesive directly to the surface of the KOVARA™ 95 in accordance with the manufacturer's recommendation for non-porous substrates.

With the continuous advancement of flooring technologies, it is impossible to list all of the products that can be effectively installed using KOVARA™ 95. If your product is not included in the list of approved floor coverings, please contact GCP Technical Services for additional information. Always follow your specific flooring manufacturer's recommendations for installation over non-porous substrates.

Perform necessary planning and layout of all flooring materials. We recommend lighter chalks as they will be clearly seen on the surface of the KOVARA™ 95. Always adjust the layout to avoid seam joints falling directly over a KOVARA™ 95 seam.

Caution should be taken to ensure the KOVARA™ 95 membrane is not cut, damaged or punctured. Some adhesives may take longer to flash off and cure compared to installations over porous concrete. Always use a new trowel with the recommended notch for each application.

transforming performance.

Do not mechanically fasten wood flooring through KOVARA™ 95. Regarding floating flooring systems, carefully follow all flooring manufacturer’s recommendations for the installation.

Initial Maintenance

Upon completion of the finished flooring installation, KOVARA™ 95 requires a minimum of 120 hours (5 days) before conducting initial ‘wet’ cleaning or maintenance. Failure to follow this requirement may result in improper adhesive curing and/or failure of the adhesive bond. Always clean and maintain flooring with neutral pH cleaning products.

Physical Properties

PROPERTY	TYPICAL VALUE	TESTING METHOD
Roll Size	5' x 144' (720 sq. ft.)	-
Minimum Basic Weight	11.5 lbs. per 100 sq. ft.	ASTM D2646
Minimum Thickness	24.0 mils	ASTM D5729
Permeance	0.084 grain h ⁻¹ ft ⁻² in Hg ⁻¹	ASTM E96
Maximum PH Allowed	12	-
Fungi and Mold Resistance	Does not sustain mold growth	ASTM G21-15
VOC	Zero VOC product	ASTM D5197
Formaldehyde	Passes	ASTM D5197
Flammability	Passes	ASTM D2859-96
Dimensional Stability	Passes	ASTM D7570
Radiant Panel	Passes	ASTM E648-10
Smoke Density	Passes	NFPA 258
Residual Indentation	Passes	ASTM F970
Acoustical rating using 6" concrete and 1/2" engineered wood, no suspended ceiling assembly		
	IIC = 51	ASTM E492-04
	STC = 52	ASTM E90-04

transforming performance.